

A P P E N D I X I:

SPECIFICATION AMENDMENTS:

Delete the text on pages 36 and 37 of the specification in favor of the following Substitute Abstract:

Substitute Abstract

Thermoplastic molding composition comprising components A, B, C and D and, if appropriate, E, F, G and H,

- A) from 1 to 97.5% by weight of at least one aromatic polycarbonate A,
- B) from 1 to 97.5% by weight of at least one graft polymer B made from b1) from 40 to 80% by weight of a graft base made from an elastomeric polymer B1, b2) from 20 to 60% by weight of a graft B2 made from b21) from 60 to 95% by weight of styrene or of substituted styrenes B21 and b22) from 5 to 40% by weight of at least one unsaturated nitrile B22,
- C) from 1 to 97.5% by weight of at least one thermoplastic copolymer C made from c1) from 60 to 85% by weight of styrene or of substituted styrenes C1 or mixtures thereof and c2) from 15 to 40% by weight of at least one unsaturated nitrile C2,
- D) from 0.5 to 50% by weight of at least one copolymer D, obtainable via reaction of d1) from 5 to 95% by weight of at least one thermoplastic methacrylate polymer D1 containing at least one type of functional groups selected from epoxy, carboxy, hydroxy, anhydride and oxazoline, with d2) from 5 to 95% by weight of at least one thermoplastic polyester D2,
- E) from 0 to 40% by weight of at least one filler E,
- F) from 0 to 2% by weight of at least one organic acid F,
- G) from 0 to 25% by weight of at least one halogen-free phosphorus compound G,
- H) from 0 to 45% by weight of other additives H.